

Gladding, McBean

TECHNICAL DATA SHEET

Lab ID. 50908

LINCOLN #60 CLAY

Please find listed below analysis on the following clay sample.

Silicon Dioxide	54.31%
Aluminum Oxide	24.49%
Ferric Oxide	1.92%
Calcium Oxide	*
Magnesium Oxide	0.06%
Sodium Oxide	0.33%
Potassium Oxide	2.02%
Titanium Dioxide	2.23%
Manganese Dioxide	0.006%
Loss on Ignition at 1750 F	9.50%
Moisture at 105 C	2.48%
Undetermined	2.65%

* Less than detection limit.



GLADDING, McBEAN
a division of PACIFIC COAST
building products

P.O. Box 97 Lincoln, California 95648
(916) 645-8937 (916) 645-3595
Fax: (916) 645-2594
www.gladdingmcbean.com

G076 1000 PR 07/09/02